

**ALLOY DESCRIPTION**

Used in medium strength structural applications where post weld heat treating is impractical. Developed in Japan as a corrosion resistant, extrudable, medium strength alloy.

**TYPICAL MECHANICAL PROPERTIES (LONGITUDINAL)**

Temper	Tensile (.500" Dia. Specimen)					Hardness Brinell 500kg 10 mm	Shear		Fatigue		Modulus	
	Ultimate		Yield		Elongation/4D %		Ultimate Shearing Strength		Endurance Limit - R.R. Moore Type		Modulus of Elasticity	
	KSI	MPa	KSI	MPa			KSI	MPa	KSI	MPa	KSI x 10 <sup>3</sup>	Gpa
T5	50	345	42	290	15	-	-	-	-	-	-	-

\*In 10E7 cycles, axially loaded specimens tested at R = 0.1

**COMPARATIVE CHARACTERISTICS**

Temper	Corrosion Resistance		Cold Workability <sup>3</sup>	Machinability <sup>3</sup>	Anodize Response <sup>3</sup>	Brazeability <sup>4</sup>	Weldability <sup>4</sup>		
	General <sup>1</sup>	Stress <sup>2</sup>					Gas	Arc	Spot
T5	C	C	C	C	B	D	B	B	B

- Ratings A through E are relative ratings in decreasing order of merit, based on exposures to sodium chloride solution by intermittent spraying or immersion. Alloys with A and B ratings can be used in industrial and seacoast atmospheres without protection. Alloys with C, D and E ratings generally should be protected at least on faying surfaces.
- Stress-corrosion cracking ratings are based on service experience and laboratory tests of specimens exposed to the 3.5% sodium chloride alternate immersion test.
  - A= No known instance of failure in service or in laboratory tests.
  - B= No known instance of failure in service; limited failures in laboratory tests of short transverse specimens.
  - C= Service failures with sustained tension stress acting in short transverse direction relative to grain structure; limited failures in laboratory tests of long transverse specimens.
  - D= Limited service failures with sustained longitudinal or long transverse
- Ratings A through D for Workability (cold), A through E for Machinability and A through C for Anodize Response, are relative ratings in decreasing order of merit.
- Ratings A through D for Weldability and Brazeability are relative ratings defined as follows:
  - A= Generally weldable by all commercial procedures and methods.
  - B= Weldable with special techniques or for specific applications that justify preliminary trials or testing to develop welding procedure and weld performance.
  - C = Limited weldability because of crack sensitivity or loss in resistance to corrosion and mechanical properties.
  - D= No commonly used welding methods have been developed.

Continued Page 2 of 2

**APPLICABLE SPECIFICATIONS**

Cold Finished	Extruded
	AMS 4157
	AMS 4159

**CHEMICAL COMPOSITION LIMITS**

										Others	
Weight %	Si	Fe	Cu	Mn	Mg	Cr	Zn	Ti	Zr	Each	Total
Minimum	-	-	-	-	0.50	-	5.0	-	0.05	-	-
Maximum	0.30	0.35	0.20	0.30	1.0	0.20	6.5	0.20	0.25	0.05	0.15

**TYPICAL PHYSICAL PROPERTIES**

Characteristic		English	Metric
Nominal Density (68 °F/20 °C)		0.103 lbs./in. <sup>3</sup>	2.84 Mg/m <sup>3</sup>
Melting Range			
Specific Heat (212 °F/100 °C)			
Coefficient of Thermal Expansion	Linear 68 °F-212 °F 20 °C-100 °C		
	Volumetric 68 °F/20 °C		
Thermal Conductivity (68 °F/20 °C)	T6, T651		
	T7, T7351		
Electrical Conductivity (68 °F/20 °C)	Equal Volume		
	Equal Weight		